

polytec High Pressure Laminate

General Information

polytec's range of Laminate and Benchtops are designed for applications such as kitchen worktops, countertops, bathroom vanities and laundry benchtops where a durable decorative surface is required.

Features

- Tough and durable
- Resistant to cracking, chipping, chemicals and reagents
- Industry relevant colour range
- Standard Laminates (Non-Postformable) and Postformable Laminates to Tight Form in most colours on 33, 39mm substrate

Note: Benchtops should be pre-drilled prior to cutouts, leaving a 10mm radius in corners. Internal corners should not be square which may cause cracking.

polytec do not grain match timberprints, stone patterns and abstract colours where a joint is required.

Environmental/Safety

polytec is committed to ensuring that its products can be manufactured, transported, stored, used, disposed and recycled with an appropriate regard for safety, health and environmental protection. We support the safe handling of our products.

Product Properties

PHYSICAL PROPERTIES	UNIT	TYPICAL PROPERTY	TEST METHOD
Density	Kg/m ³	1350 - 1450	ASTM D 792-1
Dimensional Tolerance			
Length	mm	± 5	AS/NZS 2924.1
Width	mm	± 5	
Thickness	mm	± 0.1	
Colour Stability		Blue wool standard Min 6	AS/NZS 2924.1
Thickness Swell (24hr @ 20°C)	%	≤3.5	BS EN 317
Resistance to Impact	N	>20	AS/NZS 2924.1
Resistance to Scratch	N	≥ 3	AS/NZS 2924.1
Resistance to Wear	Revolutions	≥ 350	AS/NZS 2924.1
Resistance to Steam		≥ 4	AS/NZS 2924.1
Dry Heat Resistance, 180°C			
Finishes		≥ 4	AS/NZS 2924.1
Resistance to Staining			
Group 1 + 2		≥ 5	AS/NZS 2924.1
Group 3 + 4		≥ 4	
Resistance to Boiling Water		No Visible Change	AS/NZS 2924.1
Dimensional Stability at elevated temperature	%	L ≤ 0.7 , T ≤ 1.2	AS/NZS 2924.1

Fire Tests

Classified as Group 1 in accordance with specification C1.10 section 4 of BCA.

Chemical Resistance Test Results

polytec always recommend prompt clean-up of all spills on its decorative surfaces and the surface maintained in accordance with our Care and Maintenance instructions. polytec High Pressure Laminate products should always be protected against direct sunlight as continuous exposure may cause discolouration or fading over time.

PERFORMANCE	CHEMICAL
No visible effect	Water, alcohol 96%, isopropanol, Petrol, amy1 acetate, acetone, household soap, detergents for dishwashing by hand, ammonium hydrate 10%, ketchup, cooking oil, trisodium phosphate 1%, coffee, tea, milk, acetic acid, caustic soda (<10%), citric acid 10%, wine, lipstick, grapefruit juice, wax, shoe polish, ink ballpoint pen, spirit dye pen, marking ink, hand cream
Slight Effect/No Effect if completely removed within 10-15 minutes	Hydrogen Peroxide 30%, hypochlorite bleach, hair dye, mercury chromate 2%, iodine, hydrochloric acid (<10%), phosphoric acid (10%), caustic soda (>10%)
Surface attack/necessitating immediate removal	Hydrochloric Acid (>10%), nitric acid (>10%), Sulphuric Acid (>10%)

Product Weights

THICKNESS (mm)	DENSITY (kg/m3)	TYPICAL PRODUCT WEIGHT					
		(kg/m2)	3660 x 1360	3660 x 680	1825 x 1360	1825 x 680	3660 x 1220
0.7	1400	0.9	4.46	2.23	2.23	1.11	4.00

Contact

For further information on this product contact:

Borg Manufacturing (ABN 31 003 246 357), 2 Wella Way, Somersby, NSW 2250, Australia
 Telephone: 1300 300 547 Fax: 1300 320 547

Whilst the information contained in this document is based on data, which, to the best of our knowledge, was accurate and reliable at the time of preparation, we can accept no responsibility for errors and omissions. The provision of this information should not be construed as a recommendation to use any of our products in violation of any patent rights or breach of any statute or regulation. Users are advised to make their own determination as to the suitability of this information in relation to their particular purposes and specific circumstances. Since the information contained in this document may be applied under conditions beyond our control, we can accept no responsibility for any loss or damage caused by any person acting or refraining from action as a result of this information.

Date of last update: December 2023